



© lalegno

### Dimension board

|                            |                                         |
|----------------------------|-----------------------------------------|
| <b>LENGTH</b>              | 2130 mm                                 |
| <b>WIDTH</b>               | 240 mm                                  |
| <b>TOTAL THICKNESS</b>     | 14.0 mm                                 |
| <b>THICKNESS TOP LAYER</b> | 3 mm                                    |
| <b>LAYER CONTENTS</b>      | 5 pl x 2130 mm + 2 pl<br>RL 600-2130 mm |

### Dimension pack

|                           |                     |
|---------------------------|---------------------|
| <b>PACK LENGTH</b>        | 2150 mm             |
| <b>PACK WIDTH</b>         | 245 mm              |
| <b>PACK THICKNESS</b>     | 86 mm               |
| <b>PACK WEIGHT</b>        | 19 kg               |
| <b>LAYERS/BOX</b>         | 6                   |
| <b>M<sup>2</sup>/PACK</b> | 3.07 m <sup>2</sup> |

### Dimension pallet

|                             |                       |
|-----------------------------|-----------------------|
| <b>PALLET LENGTH</b>        | 2150 mm               |
| <b>PALLET WIDTH</b>         | 740 mm                |
| <b>PALLET HEIGHT</b>        | 1150 mm               |
| <b>PALLET WEIGHT</b>        | 1045 kg               |
| <b>PACKS/PALLET</b>         | 33                    |
| <b>M<sup>2</sup>/PALLET</b> | 101.31 m <sup>2</sup> |

## CHARACTERISTICS

### Top layer

|                            |                          |
|----------------------------|--------------------------|
| <b>WOOD SPECIES</b>        | Oak                      |
| <b>LATIN NAME</b>          | Quercus Robur            |
| <b>GRADE</b>               | CLASSIC A                |
| <b>CONSTRUCTION</b>        | 3-layer                  |
| <b>THICKNESS TOP LAYER</b> | 3 mm                     |
| <b>PATTERN</b>             | 1 strip                  |
| <b>CUTTING METHOD</b>      | Zaagfineer               |
| <b>BEVEL</b>               | Micro bevel 2 long sides |
| <b>FINISH</b>              | Lacquer                  |
| <b>SURFACE STRUCTURE</b>   | Smooth                   |

### Composition of the support

|                                |             |
|--------------------------------|-------------|
| <b>SUPPORT TYPE</b>            | Hevea       |
| <b>WOOD SPECIES SUPPORT</b>    | Hevea       |
| <b>TOTAL THICKNESS SUPPORT</b> | 11 mm       |
| <b>ADHESION</b>                | Kruiselings |

### Installation

| SYSTEM            | APPLICATIONS                                                                                                                     | UNDERFLOOR HEATING |
|-------------------|----------------------------------------------------------------------------------------------------------------------------------|--------------------|
| Tongue and groove | Light household use.<br>Moderate commercial use.<br>Normal commercial use.<br>Normal household use.<br>Intensive commercial use. | Yes                |
|                   |                                                                                                                                  | <b>RE-SANDABLE</b> |
|                   |                                                                                                                                  | Yes                |

## TECHNICAL SPECIFICATIONS

|                       | Norm                | Result                 |
|-----------------------|---------------------|------------------------|
| REACTION TO FIRE      | EN 13501-1          | Dfl-S1                 |
| FORMALDEHYDE EMISSION | EN 717-1            | E1                     |
| PCP                   | CEN/TR 14823        | ≤ 5ppm                 |
| THERMAL CONDUCTIVITY  | EN 12667 / ISO 8302 | 0,11m <sup>2</sup> k/w |
| BIOLOGICAL DURABILITY | EN 335              | Class 1                |
| BREAKING STRENGTH     | EN 1533             | Pass                   |
| SLIPPERINESS          | EN 15676            | Pass                   |
| MOISTURE CONTENT      | EN 13183-1          | 7% (+/-2%)             |

## CERTIFICATION



EN 14342

