

Quanzhou Jiarun Paper Industry Co., Ltd.,				
Sanshu Industrial Park, No.666, Binhu South Road, Taivanesee Investment Zone, Quanzhou, Fujian Province, China				
Sanitary Napkin Material Analysis				
Brand			Izzy Sanitary	
Size/mm			290	330
Total Weight/g			8.50	9.50
Absorbency	Absorption/ml		170	200
Sanitary Napkin Material Analysis	Weight (g)	Non woven topsheet	0.406	0.454
		Non woven side water proof	0.663	0.758
		ADL	0.332	0.380
		Aidlaid paper	1.989	2.250
		SAP Paper	2.304	2.565
		PE backsheet	1.012	1.140
		Release paper	0.638	0.703
		PE single warp	0.570	0.608
		Glue	0.577	0.642
		Total	8.489	9.500
	Ratio (%)	Non woven topsheet	5.42%	5.34%
		Non woven side water proof	8.84%	8.92%
		ADL	4.42%	4.47%
		Aidlaid paper	26.52%	26.47%
		Sap paper	30.71%	30.18%
		PE backsheet	13.49%	13.41%
		Release paper	8.50%	8.27%
		PE single warp	7.59%	7.15%
/	/	Glue	7.70%	7.55%
/	/	Total	1.132	1.118
Absorbency Core Material Analysis	Ratio (%)	SAP paper/g	2.304	2.565
		SAP Paper Ratio/%	27.10%	27.00%
Feature			1, Hot Air Non-woven facbric 2, SAP Tissue Paper+ Airlaid paper 3, PE backsheet&PE film Wrap 4, Release Paper	



Quanzhou Jiarun Paper Industry Co., Ltd.,

Sanshu Industrial Park, No.666, Binhu South Road, Taivanesee Investment Zone, Quanzhou, Fujian Province, China

Sanitary Napkin Material Analysis

Brand			Izzy Sanitary	
Size/mm			290	330
Total Weight/g			8.50	9.50
Absorbency	Absorption/ml		170	200
Sanitary Napkin Material Analysis	Weight (g)	Non woven topsheet	0.406	0.454
		Non woven side water proof	0.663	0.758
		ADL	0.332	0.380
		Aidlaid paper	1.989	2.250
		SAP Paper	2.304	2.565
		PE backsheet	1.012	1.140
		Release paper	0.638	0.703
		PE single warp	0.570	0.608
		Glue	0.577	0.642
		Total	8.489	9.500
	Ratio (%)	Non woven topsheet	5.42%	5.34%
		Non woven side water proof	8.84%	8.92%
		ADL	4.42%	4.47%
		Aidlaid paper	26.52%	26.47%
		Sap paper	30.71%	30.18%
		PE backsheet	13.49%	13.41%
		Release paper	8.50%	8.27%
		PE single warp	7.59%	7.15%
/	/	Glue	7.70%	7.55%
/	/	Total	1.132	1.118
Absorbency Core Material Analysis	Ratio (%)	SAP paper/g	2.304	2.565
		SAP Paper Ratio/%	27.10%	27.00%
Feature			1, Hot Air Non-woven facbric 2, SAP Tissue Paper+Airlaid paper 3, PE backsheet&PE film Wrap 4, Release Paper	

